

NEW

MINI DVAS

RECOMMENDED CUTTING CONDITIONS

Material	DC	L/D	Vc	n	f
P Mild steel Carbon steel, Alloy steel	1.0	2-30	65(30-100)	20700	0.035(0.020-0.050)
	1.0	40, 50	65(30-100)	20700	0.030(0.020-0.040)
	1.5	2-30	65(30-100)	13800	0.053(0.030-0.075)
	1.5	40, 50	65(30-100)	13800	0.045(0.030-0.060)
	2.0	2-30	70(40-100)	11100	0.070(0.040-0.100)
	2.0	40, 50	70(40-100)	11100	0.060(0.040-0.080)
	2.5	2-30	70(40-100)	8900	0.088(0.050-0.125)
	2.5	40, 50	70(40-100)	8900	0.075(0.050-0.100)
	2.9	2-30	70(40-100)	7700	0.102(0.058-0.145)
2.9	40, 50	70(40-100)	7700	0.087(0.058-0.116)	
P Austenitic stainless steel, Ferritic stainless steel Ferritic and martensitic stainless steel Precipitation hardening stainless steel	1.0	2-30	60(20-100)	19100	0.025(0.010-0.040)
	1.0	40, 50	60(20-100)	19100	0.020(0.010-0.030)
	1.5	2-30	60(20-100)	12700	0.038(0.015-0.060)
	1.5	40, 50	60(20-100)	12700	0.030(0.015-0.045)
	2.0	2-30	60(20-100)	9500	0.050(0.020-0.080)
	2.0	40, 50	60(20-100)	9500	0.040(0.020-0.060)
	2.5	2-30	60(20-100)	7600	0.063(0.025-0.100)
	2.5	40, 50	60(20-100)	7600	0.050(0.025-0.075)
	2.9	2-30	60(20-100)	6600	0.073(0.029-0.116)
2.9	40, 50	60(20-100)	6600	0.058(0.029-0.087)	
K Cast iron Ductile cast iron	1.0	2-30	70(40-100)	22300	0.035(0.020-0.050)
	1.0	40, 50	70(40-100)	22300	0.030(0.020-0.040)
	1.5	2-30	70(40-100)	14900	0.053(0.030-0.075)
	1.5	40, 50	70(40-100)	14900	0.045(0.030-0.060)
	2.0	2-30	70(40-100)	11100	0.070(0.040-0.100)
	2.0	40, 50	70(40-100)	11100	0.060(0.040-0.080)
	2.5	2-30	70(40-100)	8900	0.088(0.050-0.125)
	2.5	40, 50	70(40-100)	8900	0.075(0.050-0.100)
	2.9	2-30	70(40-100)	7700	0.102(0.058-0.145)
2.9	40, 50	70(40-100)	7700	0.087(0.058-0.116)	
N Aluminium alloy	1.0	2-30	140(100-180)	31800	0.040(0.020-0.060)
	1.0	40, 50	140(100-180)	31800	0.035(0.020-0.050)
	1.5	2-30	140(100-180)	21200	0.060(0.030-0.090)
	1.5	40, 50	140(100-180)	21200	0.053(0.030-0.075)
	2.0	2-30	140(100-180)	15900	0.080(0.040-0.120)
	2.0	40, 50	140(100-180)	15900	0.070(0.040-0.100)
	2.5	2-30	140(100-180)	12700	0.100(0.050-0.150)
	2.5	40, 50	140(100-180)	12700	0.088(0.050-0.125)
	2.9	2-30	140(100-180)	11000	0.116(0.058-0.174)
2.9	40, 50	140(100-180)	11000	0.102(0.058-0.145)	

MINI DVAS

RECOMMENDED CUTTING CONDITIONS

Material	DC	L/D	Vc	n	f
Heat resistant alloy	1.0	2-30	30(10-50)	9500	0.015(0.010-0.020)
	1.0	40, 50	30(10-50)	9500	0.015(0.010-0.020)
	1.5	2-30	30(10-50)	6400	0.023(0.015-0.030)
	1.5	40, 50	30(10-50)	6400	0.023(0.015-0.030)
	2.0	2-30	30(10-50)	4800	0.030(0.020-0.040)
	2.0	40, 50	30(10-50)	4800	0.030(0.020-0.040)
	2.5	2-30	30(10-50)	3800	0.038(0.025-0.050)
	2.5	40, 50	30(10-50)	3800	0.038(0.025-0.050)
	2.9	2-30	30(10-50)	3300	0.044(0.029-0.058)
2.9	40, 50	30(10-50)	3300	0.044(0.029-0.058)	
S Titanium alloy	1.0	2-30	30(20-40)	9500	0.020(0.010-0.030)
	1.0	40, 50	30(20-40)	9500	0.020(0.010-0.030)
	1.5	2-30	30(20-40)	6400	0.030(0.015-0.045)
	1.5	40, 50	30(20-40)	6400	0.030(0.015-0.045)
	2.0	2-30	30(20-40)	4800	0.040(0.020-0.060)
	2.0	40, 50	30(20-40)	4800	0.040(0.020-0.060)
	2.5	2-30	30(20-40)	3800	0.050(0.025-0.075)
	2.5	40, 50	30(20-40)	3800	0.050(0.025-0.075)
	2.9	2-30	30(20-40)	3300	0.058(0.029-0.087)
2.9	40, 50	30(20-40)	3300	0.058(0.029-0.087)	
Cobalt chrome alloy	1.0	2-30	60(30-90)	19100	0.020(0.010-0.030)
	1.0	40, 50	60(30-90)	19100	0.020(0.010-0.030)
	1.5	2-30	60(30-90)	12700	0.030(0.015-0.045)
	1.5	40, 50	60(30-90)	12700	0.030(0.015-0.045)
	2.0	2-30	60(30-90)	9500	0.040(0.020-0.060)
	2.0	40, 50	60(30-90)	9500	0.040(0.020-0.060)
	2.5	2-30	60(30-90)	7600	0.050(0.025-0.075)
	2.5	40, 50	60(30-90)	7600	0.050(0.025-0.075)
	2.9	2-30	60(30-90)	6600	0.058(0.029-0.087)
2.9	40, 50	60(30-90)	6600	0.058(0.029-0.087)	

1. This recommended condition is only when using internal coolant.
2. Check the condition of chips and perform step machining if necessary. * Reference of step length: 0.2 to 1.0 DC
3. Adjust the cutting conditions according to machine tool and workpiece clamp rigidity and machining geometry, etc.
4. Machining depths exceeding flute length (LU) are not recommend.
5. Clamp the drill so that the drill runout is within 0.003 mm.
6. Do not clamp the flute part of the drill.