

RECOMMENDED CUTTING CONDITIONS

Work Material	Hardness	Cutting Speed (m/min)			Breaker	Feed (mm/rev)					
		For l/d=2, 3		For l/d=4		Drill Diameter (mm)					
		(Ø12–Ø14.5)	(Ø15–)	(Ø16–)		Ø12–Ø14.5	Ø15–Ø22.5	Ø23–Ø34	Ø35–Ø48	Ø49–Ø56	
P	Mild Steel	$\leq 180\text{HB}$	150 (100–200)	200 (150–300)	140 (100–200)	U1	0.06 (0.04–0.10)	0.07 (0.04–0.10)	0.08 (0.04–0.10)	0.10 (0.04–0.12)	0.08 (0.04–0.10)
						U2	0.06 (0.04–0.10)	0.08 (0.04–0.12)	0.10 (0.04–0.12)	0.12 (0.04–0.14)	0.10 (0.04–0.12)
						U3	—	0.08 (0.04–0.12)	0.10 (0.04–0.12)	0.12 (0.04–0.14)	0.10 (0.04–0.12)
	Carbon Steel	180–280HB	120 (80–160)	150 (120–180)	100 (80–120)	U1	0.06 (0.04–0.10)	0.09 (0.06–0.12)	0.12 (0.08–0.14)	0.15 (0.08–0.18)	0.12 (0.08–0.14)
						U2	0.06 (0.04–0.10)	0.12 (0.06–0.14)	0.14 (0.08–0.18)	0.17 (0.08–0.20)	0.14 (0.08–0.18)
						U3	—	0.12 (0.06–0.14)	0.14 (0.08–0.18)	0.17 (0.08–0.20)	0.14 (0.08–0.18)
	Alloy Steel	180–280HB	120 (80–160)	150 (120–180)	100 (80–120)	U1	0.06 (0.04–0.10)	0.08 (0.06–0.10)	0.09 (0.06–0.12)	0.11 (0.06–0.14)	0.09 (0.06–0.12)
						U2	0.06 (0.04–0.10)	0.10 (0.06–0.12)	0.12 (0.08–0.16)	0.14 (0.08–0.18)	0.12 (0.08–0.16)
						U3	—	0.10 (0.06–0.12)	0.12 (0.08–0.16)	0.14 (0.08–0.18)	0.12 (0.08–0.16)
M	Stainless Steel	$\leq 200\text{HB}$	100 (80–120)	150 (120–200)	110 (80–140)	U1	0.07 (0.04–0.10)	0.07 (0.04–0.10)	0.08 (0.04–0.10)	0.10 (0.04–0.12)	0.08 (0.04–0.10)
						U2	0.07 (0.04–0.10)	0.08 (0.04–0.12)	0.10 (0.04–0.14)	0.12 (0.04–0.16)	0.10 (0.04–0.14)
						U3	—	0.08 (0.04–0.12)	0.10 (0.04–0.14)	0.12 (0.04–0.16)	0.10 (0.04–0.14)
K	Cast Iron	Tensile Strength $\leq 350\text{MPa}$	120 (80–160)	150 (120–180)	140 (110–160)	U1	0.07 (0.06–0.10)	0.07 (0.06–0.10)	0.10 (0.04–0.14)	0.10 (0.06–0.14)	0.10 (0.06–0.14)
						U2	0.07 (0.06–0.10)	0.15 (0.10–0.18)	0.20 (0.10–0.25)	0.20 (0.10–0.25)	0.20 (0.10–0.25)
						U3	—	0.15 (0.10–0.18)	0.20 (0.10–0.25)	0.20 (0.10–0.25)	0.20 (0.10–0.25)
	Ductile Cast Iron	Tensile Strength $\leq 450\text{MPa}$	120 (80–150)	150 (120–180)	100 (80–120)	U1	0.06 (0.04–0.10)	0.07 (0.06–0.10)	0.10 (0.06–0.14)	0.10 (0.06–0.14)	0.10 (0.06–0.14)
						U2	0.06 (0.04–0.10)	0.12 (0.08–0.14)	0.15 (0.08–0.20)	0.18 (0.08–0.20)	0.15 (0.08–0.20)
						U3	—	0.12 (0.08–0.14)	0.15 (0.08–0.20)	0.18 (0.08–0.20)	0.15 (0.08–0.20)

(Note) When using drills for l/d = 4, the feed should be reduced to 80% of the above recommendations.

CUTTING RESISTANCE

Workpiece : DIN X5CrNi189 (220HB) Cutting Speed : 150m/min Insert : U2 Breaker

