


VQJCS

RECOMMENDED CUTTING CONDITIONS

SIDE MILLING

Material	DC	Vc	n	Vf	ap	ae	hm	h max	
P Carbon steel, Alloy steel, Mild steel	6	200	10600	1800	18	0.9	0.010	0.019	
	8	200	8000	1800	24	1.2	0.013	0.025	
	10	200	6400	1700	30	1.5	0.016	0.029	
	12	200	5300	1700	36	1.8	0.019	0.035	
	16	200	4000	1400	48	2.4	0.020	0.039	
	20	200	3200	1200	60	3.0	0.023	0.043	
	Pre-hardened steel, Carbon steel, Alloy steel, Alloy tool steel	6	180	9500	1500	18	0.9	0.009	0.017
		8	180	7200	1500	24	1.2	0.012	0.023
		10	180	5700	1400	30	1.5	0.015	0.028
		12	180	4800	1400	36	1.8	0.017	0.032
16		180	3600	1200	48	2.4	0.018	0.035	
M Austenitic, Ferritic and Martensitic stainless steels,	6	120	6400	1000	18	0.45	0.006	0.012	
	8	120	4800	1000	24	0.6	0.008	0.016	
	10	120	3800	900	30	0.75	0.010	0.019	
S Titanium alloys	12	120	3200	800	36	0.9	0.011	0.021	
	16	120	2400	700	48	1.2	0.012	0.023	
	20	120	1900	600	60	1.5	0.013	0.026	
M Hardened stainless steels, Cobalt chromium alloy	6	100	5300	800	18	0.45	0.006	0.012	
	8	100	4000	800	24	0.6	0.008	0.016	
	10	100	3200	800	30	0.75	0.01	0.019	
	12	100	2700	700	36	0.9	0.011	0.021	
	16	100	2000	600	48	1.2	0.012	0.023	
N Copper, Copper alloy	20	100	1600	500	60	1.5	0.013	0.026	
	6	220	11700	2100	18	0.9	0.010	0.019	
	8	220	8800	2100	24	1.2	0.014	0.026	
	10	220	7000	1800	30	1.5	0.015	0.028	
	12	220	5800	1800	36	1.8	0.018	0.034	
S Heat resistant alloys	16	220	4400	1500	48	2.4	0.020	0.038	
	20	220	3500	1400	60	3.0	0.022	0.042	
	6	40	2100	200	18	0.18	0.002	0.004	
	8	40	1600	200	24	0.24	0.003	0.006	
	10	40	1300	200	30	0.3	0.003	0.007	
	12	40	1100	100	36	0.36	0.003	0.007	
	16	40	800	100	48	0.48	0.004	0.007	
	20	40	600	100	60	0.6	0.004	0.007	



1. SMART MIRACLE coating has very low electrical conductivity; therefore, an electrical contact type of tool setter may not work. When measuring the tool length, please use a mechanical contact type or a laser tool setter.
2. The irregular pitch flute end mill has a larger effect on controlling vibration when compared to standard end mills. However, if the rigidity of the machine or the workpiece material installation is poor, vibration or abnormal sounds can occur. In that case, please adjust the revolution, feed rate and depth of cut.
3. The revolution and feed rate can be increased with a smaller depth of cut.
4. For stainless steel, titanium alloys and heat resistant alloys, the use of water-soluble coolant is effective.