

RECOMMENDED CUTTING CONDITIONS

Work Material	Mild Steel ($\leq 180\text{HB}$)				Carbon steel, Alloy steel (180—280HB)			
	Ck10				Ck45, 42CrMo4			
Coolant type	Water insoluble cutting oil				Water insoluble cutting oil			
Drill Dia. (mm)	Cutting Speed (m/min)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	Table Feed (mm/min)	Cutting Speed (m/min)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	Table Feed (mm/min)
0.8	50	19800	0.01 (0.005—0.016)	195	40	15900	0.01 (0.005—0.016)	155
1.0	50	15900	0.01 (0.007—0.020)	155	40	12700	0.01 (0.007—0.020)	125
1.2	60	15900	0.015 (0.008—0.024)	235	50	13200	0.015 (0.008—0.024)	195
1.6	60	11900	0.02 (0.011—0.032)	235	50	9900	0.02 (0.011—0.032)	195
2.0	60	9500	0.025 (0.013—0.040)	235	50	7900	0.025 (0.013—0.040)	195
2.5	70	8900	0.03 (0.017—0.050)	265	60	7600	0.03 (0.017—0.050)	225
3.0	70	7400	0.04 (0.020—0.060)	295	60	6300	0.04 (0.020—0.060)	250
Work Material	Carbon steel, Alloy steel (280—350HB)				Austenitic Stainless Steel ($\leq 200\text{HB}$)			
	36CrNiMo4				X5CrNi1810, X5CrNiMo17-12-2			
Coolant type	Water insoluble cutting oil				Water insoluble cutting oil			
Drill Dia. (mm)	Cutting Speed (m/min)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	Table Feed (mm/min)	Cutting Speed (m/min)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	Table Feed (mm/min)
0.8	30	11900	0.005 (0.004—0.005)	55	30	11900	0.01 (0.005—0.016)	115
1.0	30	9500	0.005 (0.005—0.007)	45	30	9500	0.01 (0.007—0.020)	95
1.2	40	10600	0.005 (0.006—0.008)	50	30	7900	0.015 (0.008—0.024)	115
1.6	40	7900	0.01 (0.008—0.011)	75	40	7900	0.02 (0.011—0.032)	155
2.0	40	6300	0.01 (0.010—0.013)	60	40	6300	0.025 (0.013—0.040)	155
2.5	50	6300	0.015 (0.013—0.017)	90	40	5000	0.03 (0.017—0.050)	150
3.0	50	5300	0.015 (0.015—0.020)	75	40	4200	0.04 (0.020—0.060)	165
Work Material	Gray Cast Iron ($\leq 350\text{MPa}$)				Ductile Cast Iron ($\leq 450\text{MPa}$)			
	GG30				GGG45			
Coolant type	Water insoluble cutting oil • Water soluble cutting oil				Water insoluble cutting oil • Water soluble cutting oil			
Drill Dia. (mm)	Cutting Speed (m/min)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	Table Feed (mm/min)	Cutting Speed (m/min)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	Table Feed (mm/min)
0.8	50	19800	0.01 (0.008—0.016)	195	40	15900	0.005 (0.005—0.008)	75
1.0	50	15900	0.015 (0.010—0.020)	235	40	12700	0.005 (0.007—0.010)	60
1.2	60	15900	0.015 (0.012—0.024)	235	50	13200	0.01 (0.008—0.012)	130
1.6	60	11900	0.02 (0.016—0.032)	235	50	9900	0.01 (0.011—0.016)	95
2.0	60	9500	0.03 (0.020—0.040)	285	50	7900	0.015 (0.013—0.020)	115
2.5	70	8900	0.035 (0.025—0.050)	310	60	7600	0.02 (0.017—0.025)	150
3.0	70	7400	0.045 (0.030—0.060)	330	60	6300	0.025 (0.020—0.030)	155
Work Material	Aluminium Alloy (Si<5%)				Copper, Copper alloy			
Coolant type	Water insoluble cutting oil • Water soluble cutting oil				Water insoluble cutting oil • Water soluble cutting oil			
Drill Dia. (mm)	Cutting Speed (m/min)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	Table Feed (mm/min)	Cutting Speed (m/min)	Revolution (min^{-1})	Feed rate (Min.—Max.) (mm/rev)	Table Feed (mm/min)
0.8	50	19800	0.01 (0.008—0.016)	195	40	15900	0.01 (0.008—0.016)	155
1.0	60	19000	0.015 (0.010—0.020)	285	50	15900	0.015 (0.010—0.020)	235
1.2	70	18500	0.015 (0.012—0.024)	275	60	15900	0.015 (0.012—0.024)	235
1.6	80	15900	0.02 (0.016—0.032)	315	70	13900	0.02 (0.016—0.032)	275
2.0	90	14300	0.03 (0.020—0.040)	425	80	12700	0.03 (0.020—0.040)	380
2.5	100	12700	0.035 (0.025—0.050)	440	90	11400	0.035 (0.025—0.050)	395
3.0	100	10600	0.045 (0.030—0.060)	475	100	10600	0.045 (0.030—0.060)	475

1) For safety and success, High pressure coolant is required. (Minimum coolant pressure=1,000PSI)

2) Coolant filter must be less than 5 microns. Fine filtration is necessary to prevent blockage of the coolant holes.

3) A pilot hole or guide bushing is required.