

RECOMMENDED CUTTING CONDITIONS

Work Material	Stainless steel				Carbon steel Cf53, Alloy steel 070M55, Cast iron, Copper, Copper alloy	Structural steel, Aluminium alloy		
	Austenitic X5CrNi1810 X5CrNiMo17122		Martensitic, Ferritic X10CrAl18					
Drill Dia. (mm)	Revolution (min ⁻¹)	Feed rate (mm/rev)	Revolution (min ⁻¹)	Feed rate (mm/rev)	Revolution (min ⁻¹)	Feed rate (mm/rev)	Revolution (min ⁻¹)	Feed rate (mm/rev)
0.5	7600	0.01	8800	0.01	11250	0.01	15000	0.02
1.0	4800	0.02	6300	0.05	10000	0.05	12000	0.05
2.0	2400	0.04	3200	0.06	5500	0.09	6400	0.09
3.0	1600	0.07	2100	0.10	3700	0.13	4300	0.13
4.0	1200	0.09	1600	0.10	2800	0.15	3200	0.15
5.0	950	0.12	1300	0.13	2200	0.18	2600	0.18
6.0	800	0.14	1100	0.15	1800	0.20	2100	0.19
8.0	600	0.18	800	0.18	1400	0.22	1600	0.24
10.0	480	0.22	640	0.21	1100	0.25	1300	0.28
12.0	400	0.24	530	0.25	930	0.30	1100	0.34
13.0	370	0.26	490	0.28	860	0.32	1000	0.36
14.0	340	0.30	450	0.27	730	0.31	930	0.36
15.0	320	0.31	425	0.28	680	0.32	870	0.38
16.0	300	0.32	400	0.30	640	0.34	820	0.42
18.0	270	0.34	350	0.32	570	0.36	725	0.43
20.0	240	0.36	320	0.35	510	0.38	660	0.45

- 1) Please reduce the revolution and feed rate when the workpiece clamping lacks rigidity or the machine has limitations.
- 2) Please use a collet type drill chuck.
- 3) Use sufficient cutting fluid.
- 4) Do not peck drill and reduce the cutting conditions when drilling depths exceed 3xD (D : drill diameter).

The above-mentioned cutting conditions are standard when using water-soluble cutting fluid.
Please reduce the revolutions when using non-water-soluble cutting fluid.