

MP3C

RECOMMENDED CUTTING CONDITIONS

CORNER AND HOLE CHAMFERING

Material	DC	Vc	n	Vf	Corner chamfering	Hole chamfering	
					ap		
P Carbon steel, Ductile cast iron, Non-alloy steel (C≥0.55%)	2	100	16000	1400	≤ 0.6	≤ 0.4	
	4	100	8000	720	≤ 1.2	≤ 0.8	
	6	100	5300	480	≤ 1.8	≤ 1.2	
	8	100	4000	360	≤ 2.4	≤ 1.6	
	10	100	3200	290	≤ 2.5	≤ 2.0	
	12	100	2700	240	≤ 2.5	≤ 2.4	
	Alloy steel (325HB) (38–45HRC)	2	70	11000	890	≤ 0.6	≤ 0.4
		4	70	5600	450	≤ 1.2	≤ 0.8
		6	70	3700	300	≤ 1.8	≤ 1.2
		8	70	2800	230	≤ 2.4	≤ 1.6
		10	70	2200	180	≤ 2.5	≤ 2.0
		12	70	1900	150	≤ 2.5	≤ 2.4
M Austenitic stainless, Titanium alloy	2	60	9500	680	≤ 0.6	≤ 0.4	
	4	60	4800	350	≤ 1.2	≤ 0.8	
	6	60	3200	230	≤ 1.8	≤ 1.2	
	8	60	2400	170	≤ 2.4	≤ 1.6	
	S	10	60	1900	140	≤ 2.5	≤ 2.0
		12	60	1600	120	≤ 2.5	≤ 2.4
H Hardened steel (45–55HRC)	2	50	8000	480	≤ 0.6	≤ 0.4	
	4	50	4000	240	≤ 1.2	≤ 0.8	
	6	50	2700	160	≤ 1.8	≤ 1.2	
	8	50	2000	120	≤ 2.4	≤ 1.6	
	10	50	1600	96	≤ 2.5	≤ 2.0	
	12	50	1300	78	≤ 2.5	≤ 2.4	

1. For austenitic stainless steel the use of water-soluble coolant is effective.
2. The revolution and feed rate can be increased with a smaller depth of cut.
3. Vibration may occur if the rigidity of machine or workpiece material is low.
In this case, please reduce the revolution and feed rate proportionately.

MP3C**V-GROOVING**

Material		DC	Vc	n	Vf	ap
P	Carbon steel, Ductile cast iron, Non-alloy steel (C>0.55%)	2	80	13000	940	≤ 1.4
		4	80	6400	460	≤ 2.8
		6	80	4200	300	≤ 4.2
		8	80	3200	230	≤ 5.6
		10	80	2500	180	≤ 7.0
		12	80	2100	150	≤ 8.4
	Alloy steel (325HB) (38-45HRC)	2	60	9500	620	≤ 1.4
		4	60	4800	310	≤ 2.8
		6	60	3200	210	≤ 4.2
		8	60	2400	160	≤ 5.6
		10	60	1900	120	≤ 7.0
		12	60	1600	100	≤ 8.4
M	Austenitic stainless, Titanium alloy	2	50	8000	460	≤ 1.4
		4	50	4000	230	≤ 2.8
		6	50	2700	160	≤ 4.2
S		8	50	2000	120	≤ 5.6
		10	50	1600	92	≤ 7.0
		12	50	1300	75	≤ 8.4
H	Hardened steel (45-55HRC)	2	40	6400	310	≤ 1.4
		4	40	3200	150	≤ 2.8
		6	40	2100	100	≤ 4.2
		8	40	1600	77	≤ 5.6
		10	40	1300	62	≤ 7.0
		12	40	1100	53	≤ 8.4

1. For austenitic stainless steel the use of water-soluble coolant is effective.
2. The revolution and feed rate can be increased with a smaller depth of cut.
3. Vibration may occur if the rigidity of machine or workpiece material is low.
In this case, please reduce the revolution and feed rate proportionately.