MC / MP7100 SERIES

RECOMMENDED CUTTING CONDITIONS

NEGATIVE INSERTS (FOR EXTERNAL TURNING)

	Material	Hardness	Cutting mode		Priority	Grade		Vc	f	ap
M	Austenitic stainless steel	<200 HB	●	L	1	MC7115	LM	185 – 295	0.10 – 0.35	0.3 – 2.0
			●	L	2	MC7125	LM	175 – 240	0.10 – 0.35	0.3 – 2.0
			●	M	1	MC7115	MM	170 – 270	0.15 – 0.45	0.7 – 5.0
			●	R	1	MC7115	RM	160 – 255	0.25 – 0.55	1.5 – 6.0
			●	H	1	MC7125	HL	135 – 185	0.30 – 0.70	3.0 – 7.5
			◐	L	1	MC7125	LM	175 – 240	0.10 – 0.35	0.3 – 2.0
			◐	M	1	MC7125	MM	160 – 220	0.15 – 0.45	0.7 – 5.0
			◐	M	2	MC7125	GM	160 – 220	0.16 – 0.50	0.5 – 4.0
			◐	M	3	MC7125	MA	160 – 220	0.20 – 0.50	0.3 – 4.0
			◐	M	4	MP7135	GM	120 – 155	0.16 – 0.50	0.5 – 4.0
			◐	M	5	MP7135	MM	120 – 155	0.15 – 0.45	0.7 – 5.0
			◐	M	6	MP7135	MA	120 – 155	0.20 – 0.50	0.3 – 4.0
			◐	R	1	MC7125	RM	150 – 205	0.25 – 0.55	1.5 – 6.0
			◐	R	2	MP7135	RM	110 – 145	0.25 – 0.55	1.5 – 6.0
			◐	R	3	MP7135	GH	110 – 145	0.25 – 0.60	1.5 – 6.0
			◐	H	1	MC7125	HL	135 – 185	0.30 – 0.70	3.0 – 7.5
			◐	H	2	MC7125	HM	135 – 185	0.50 – 1.10	2.0 – 10.0
			✣	L	1	MP7135	LM	130 – 170	0.10 – 0.35	0.3 – 2.0
			✣	L	2	MP7135	SH	130 – 170	0.10 – 0.40	0.3 – 2.0
			✣	M	1	MP7135	GM	120 – 155	0.16 – 0.50	0.5 – 4.0
			✣	M	2	MP7135	MM	120 – 155	0.15 – 0.45	0.7 – 5.0
			✣	M	3	MP7135	MA	120 – 155	0.20 – 0.50	0.3 – 4.0
			✣	R	1	MP7135	RM	110 – 145	0.25 – 0.55	1.5 – 6.0
			✣	R	2	MP7135	GH	110 – 145	0.25 – 0.60	1.5 – 6.0
			✣	H	1	MC7125	HL	135 – 185	0.30 – 0.70	3.0 – 7.5
			✣	H	2	MC7125	HM	135 – 185	0.50 – 1.10	2.0 – 10.0
		200 HB	●	L	1	MC7115	LM	155 – 245	0.10 – 0.35	0.3 – 2.0
			●	L	2	MC7125	LM	145 – 200	0.10 – 0.35	0.3 – 2.0
			●	M	1	MC7115	MM	140 – 225	0.15 – 0.45	0.7 – 0.5
			●	R	1	MC7115	RM	135 – 215	0.25 – 0.55	1.5 – 6.0
			●	H	1	MC7125	HL	110 – 155	0.30 – 0.70	3.0 – 7.5
			●	H	2	MC7125	HM	110 – 155	0.50 – 1.10	2.0 – 10.0
			◐	L	1	MC7125	LM	145 – 200	0.10 – 0.35	0.3 – 2.0
			◐	M	1	MC7125	MM	130 – 180	0.15 – 0.45	0.7 – 5.0
			◐	M	2	MC7125	GM	130 – 180	0.16 – 0.50	0.5 – 4.0
			◐	M	3	MC7125	MA	130 – 180	0.20 – 0.50	0.3 – 4.0
			◐	M	4	MP7135	GM	100 – 130	0.16 – 0.50	0.5 – 4.0
			◐	M	5	MP7135	MM	100 – 130	0.15 – 0.45	0.7 – 5.0
			◐	M	6	MP7135	MA	100 – 130	0.20 – 0.50	0.3 – 4.0
			◐	R	1	MC7125	RM	125 – 175	0.25 – 0.55	1.5 – 6.0
			◐	R	2	MP7135	RM	95 – 120	0.25 – 0.55	1.5 – 6.0
			◐	R	3	MP7135	GH	95 – 120	0.25 – 0.60	1.5 – 6.0
			◐	H	1	MC7125	HL	110 – 155	0.30 – 0.70	3.0 – 7.5
			◐	H	2	MC7125	HM	110 – 155	0.50 – 1.10	2.0 – 10.0
			✣	L	1	MP7135	LM	110 – 140	0.10 – 0.35	0.3 – 2.0
			✣	L	2	MP7135	SH	110 – 140	0.10 – 0.40	0.3 – 2.0
			✣	M	1	MP7135	GM	100 – 130	0.16 – 0.50	0.5 – 4.0
			✣	M	2	MP7135	MM	100 – 130	0.15 – 0.45	0.7 – 5.0
			✣	M	3	MP7135	MA	100 – 130	0.20 – 0.50	0.3 – 4.0
			✣	R	1	MP7135	RM	95 – 120	0.25 – 0.55	1.5 – 6.0
			✣	R	2	MP7135	GH	95 – 120	0.25 – 0.60	1.5 – 6.0
			✣	H	1	MC7125	HL	110 – 155	0.30 – 0.70	3.0 – 7.5
			✣	H	2	MC7125	HM	110 – 155	0.50 – 1.10	2.0 – 10.0

1. Recommended cutting conditions for 5° / 7° / 11° positive inserts are provided as a guideline only.
   Verify the recommended conditions for each boring bar as cutting conditions for internal machining will vary depending on the length of overhang.

Cutting Conditions : ● : Stable cutting ◐ : General cutting ✣ : Unstable cutting

MC / MP7100 SERIES – NEGATIVE INSERTS (FOR EXTERNAL TURNING)

Material		Hardness	Cutting mode		Priority	Grade		Vc	f	ap
M	Ferritic and martensitic Stainless steel	<200 HB	●	L	1	MC7115	LM	185 – 295	0.10 – 0.35	0.3 – 2.0
			●	L	2	MC7125	LM	175 – 240	0.10 – 0.35	0.3 – 2.0
			●	M	1	MC7115	MM	170 – 270	0.15 – 0.45	0.7 – 5.0
			●	R	1	MC7115	RM	160 – 255	0.25 – 0.55	1.5 – 6.0
			●	H	1	MC7125	HL	135 – 185	0.30 – 0.70	3.0 – 7.5
			●	H	2	MC7125	HM	135 – 185	0.50 – 1.10	2.0 – 10.0
			◐	L	1	MC7125	LM	175 – 240	0.10 – 0.35	0.3 – 2.0
			◐	M	1	MC7125	MM	160 – 220	0.15 – 0.45	0.7 – 5.0
			◐	M	2	MC7125	GM	160 – 220	0.16 – 0.50	0.5 – 4.0
			◐	M	3	MC7125	MA	160 – 220	0.20 – 0.50	0.3 – 4.0
			◐	M	4	MP7135	GM	120 – 155	0.16 – 0.50	0.5 – 4.0
			◐	M	5	MP7135	MM	120 – 155	0.15 – 0.45	0.7 – 5.0
			◐	M	6	MP7135	MA	120 – 155	0.20 – 0.50	0.3 – 4.0
			◐	R	1	MC7125	RM	150 – 205	0.25 – 0.55	1.5 – 6.0
			◐	R	2	MP7135	RM	110 – 145	0.25 – 0.55	1.5 – 6.0
			◐	R	3	MP7135	GH	110 – 145	0.25 – 0.60	1.5 – 6.0
			◐	H	1	MC7125	HL	135 – 185	0.30 – 0.70	3.0 – 7.5
			◐	H	2	MC7125	HM	135 – 185	0.50 – 1.10	2.0 – 10.0
			✣	L	1	MP7135	LM	130 – 170	0.10 – 0.35	0.3 – 2.0
			✣	L	2	MP7135	SH	130 – 170	0.10 – 0.40	0.3 – 2.0
			✣	M	1	MP7135	GM	120 – 155	0.16 – 0.50	0.5 – 4.0
			✣	M	2	MP7135	MM	120 – 155	0.15 – 0.45	0.7 – 5.0
			✣	M	3	MP7135	MA	120 – 155	0.20 – 0.50	0.3 – 4.0
			✣	R	1	MP7135	RM	110 – 145	0.25 – 0.55	1.5 – 6.0
			✣	R	2	MP7135	GH	110 – 145	0.25 – 0.60	1.5 – 6.0
			✣	H	1	MC7125	HL	135 – 185	0.30 – 0.70	3.0 – 7.5
			✣	H	2	MC7125	HM	135 – 185	0.50 – 1.10	2.0 – 10.0
		>200 HB	●	L	1	MC7115	LM	155 – 245	0.10 – 0.35	0.3 – 2.0
			●	L	2	MC7125	LM	145 – 200	0.10 – 0.35	0.3 – 2.0
			●	M	1	MC7115	MM	140 – 225	0.15 – 0.45	0.7 – 5.0
			●	R	1	MC7115	RM	135 – 215	0.25 – 0.55	1.5 – 6.0
			●	H	1	MC7125	HL	110 – 155	0.30 – 0.70	3.0 – 7.5
			●	H	2	MC7125	HM	110 – 155	0.50 – 1.10	2.0 – 10.0
			◐	L	1	MC7125	LM	145 – 200	0.10 – 0.35	0.3 – 2.0
			◐	M	1	MC7125	MM	130 – 180	0.15 – 0.45	0.7 – 5.0
			◐	M	2	MC7125	GM	130 – 180	0.16 – 0.50	0.5 – 4.0
			◐	M	3	MC7125	MA	130 – 180	0.20 – 0.50	0.3 – 4.0
			◐	M	4	MP7135	GM	100 – 130	0.16 – 0.50	0.5 – 4.0
			◐	M	5	MP7135	MM	100 – 130	0.15 – 0.45	0.7 – 5.0
			◐	M	6	MP7135	MA	100 – 130	0.20 – 0.50	0.3 – 4.0
			◐	R	1	MC7125	RM	125 – 175	0.25 – 0.55	1.5 – 6.0
			◐	H	1	MC7125	HL	110 – 155	0.30 – 0.70	3.0 – 7.5
			◐	H	2	MC7125	HM	110 – 155	0.50 – 1.10	2.0 – 10.0
			✣	L	1	MP7135	LM	110 – 140	0.10 – 0.35	0.3 – 2.0
			✣	L	2	MP7135	SH	110 – 140	0.10 – 0.40	0.3 – 2.0
			✣	M	1	MP7135	GM	100 – 130	0.16 – 0.50	0.5 – 4.0
			✣	M	2	MP7135	MM	100 – 130	0.15 – 0.45	0.7 – 5.0
			✣	M	3	MP7135	MA	100 – 130	0.20 – 0.50	0.3 – 4.0
			✣	R	1	MP7135	RM	95 – 120	0.25 – 0.55	1.5 – 6.0
			✣	R	2	MP7135	GH	95 – 120	0.25 – 0.60	1.5 – 6.0
			✣	H	1	MC7125	HL	110 – 155	0.30 – 0.70	3.0 – 7.5
			✣	H	2	MC7125	HM	110 – 155	0.50 – 1.10	2.0 – 10.0

1. Recommended cutting conditions for 5° / 7° / 11° positive inserts are provided as a guideline only.
   Verify the recommended conditions for each boring bar as cutting conditions for internal machining will vary depending on the length of overhang.

Cutting Conditions : ● : Stable cutting ◐ : General cutting ✣ : Unstable cutting

MC/MP7100 SERIES – NEGATIVE INSERTS (FOR EXTERNAL TURNING)

	Material	Hardness	Cutting mode	F L M R H	Priority	Grade		Vc	f	ap
M	Two-phase stainless steel	<280 HB	●	L	1	MP7135	LM	85 – 115	0.10 – 0.35	0.3 – 2.0
			●	L	2	MP7135	SH	85 – 115	0.10 – 0.40	0.3 – 2.0
			●	L	3	MC7125	LM	115 – 160	0.10 – 0.35	0.3 – 2.0
			●	L	4	MC7115	LM	125 – 200	0.10 – 0.35	0.3 – 2.0
			●	M	1	MP7135	GM	80 – 105	0.16 – 0.50	0.5 – 4.0
			●	M	2	MP7135	MM	80 – 105	0.15 – 0.45	0.7 – 5.0
			●	M	3	MP7135	MA	80 – 105	0.20 – 0.50	0.3 – 4.0
			●	M	4	MC7125	MM	105 – 145	0.15 – 0.45	0.7 – 5.0
			●	M	5	MC7125	GM	105 – 145	0.16 – 0.50	0.5 – 4.0
			●	M	6	MC7125	MA	105 – 145	0.20 – 0.50	0.3 – 4.0
			●	M	7	MC7115	MM	115 – 180	0.15 – 0.45	0.7 – 5.0
			●	R	1	MP7135	RM	75 – 100	0.25 – 0.55	1.5 – 6.0
			●	R	2	MP7135	GH	75 – 100	0.25 – 0.60	1.5 – 6.0
			●	R	3	MC7125	RM	100 – 140	0.25 – 0.55	1.5 – 6.0
			●	H	1	MC7125	HL	90 – 125	0.30 – 0.70	3.0 – 7.5
			●	H	2	MC7125	HM	90 – 125	0.50 – 1.10	2.0 – 10.0
			◐	L	1	MP7135	LM	85 – 115	0.10 – 0.35	0.3 – 2.0
			◐	L	2	MP7135	SH	85 – 115	0.10 – 0.40	0.3 – 2.0
			◐	L	3	MC7125	LM	115 – 160	0.10 – 0.35	0.3 – 2.0
			◐	M	1	MP7135	GM	80 – 105	0.16 – 0.50	0.5 – 4.0
			◐	M	2	MP7135	MM	80 – 105	0.15 – 0.45	0.7 – 5.0
			◐	M	3	MP7135	MA	80 – 105	0.20 – 0.50	0.3 – 4.0
			◐	M	4	MC7125	MM	105 – 145	0.15 – 0.45	0.7 – 5.0
			◐	M	5	MC7125	GM	105 – 145	0.16 – 0.50	0.5 – 4.0
			◐	M	6	MC7125	MA	105 – 145	0.20 – 0.50	0.3 – 4.0
			◐	R	1	MP7135	RM	75 – 100	0.25 – 0.55	1.5 – 6.0
			◐	R	2	MP7135	GH	75 – 100	0.25 – 0.60	1.5 – 6.0
			◐	R	3	MC7125	RM	100 – 140	0.25 – 0.55	1.5 – 6.0
			◐	H	1	MC7125	HL	90 – 125	0.30 – 0.70	3.0 – 7.5
			◐	H	2	MC7125	HM	90 – 125	0.50 – 1.10	2.0 – 10.0
			✣	L	1	MP7135	LM	85 – 115	0.10 – 0.35	0.3 – 2.0
			✣	L	2	MP7135	SH	85 – 115	0.10 – 0.40	0.3 – 2.0
			✣	M	1	MP7135	GM	80 – 105	0.16 – 0.50	0.5 – 4.0
			✣	M	2	MP7135	MM	80 – 105	0.15 – 0.45	0.7 – 5.0
			✣	M	3	MP7135	MA	80 – 105	0.20 – 0.50	0.3 – 4.0
			✣	R	1	MP7135	RM	75 – 100	0.25 – 0.55	1.5 – 6.0
			✣	R	2	MP7135	GH	75 – 100	0.25 – 0.60	1.5 – 6.0
			✣	H	1	MC7125	HL	90 – 125	0.30 – 0.70	3.0 – 7.5
			✣	H	2	MC7125	HM	90 – 125	0.50 – 1.10	2.0 – 10.0

1. Recommended cutting conditions for 5° / 7° / 11° positive inserts are provided as a guideline only.
   Verify the recommended conditions for each boring bar as cutting conditions for internal machining will vary depending on the length of overhang.

Cutting Conditions : ● : Stable cutting ◐ : General cutting ✣ : Unstable cutting

MC/MP7100 SERIES – NEGATIVE INSERTS (FOR EXTERNAL TURNING)

	Material	Hardness	Cutting mode	F L M R H	Priority	Grade		Vc	f	ap
M	Precipitation-hardening stainless steel	450 HB	●	L	1	MC7115	LM	110 – 165	0.10 – 0.35	0.3 – 2.0
			●	L	2	MC7125	LM	95 – 120	0.10 – 0.35	0.3 – 2.0
			●	M	1	MC7115	MM	100 – 150	0.15 – 0.45	0.7 – 5.0
			●	R	1	MC7115	RM	95 – 140	0.25 – 0.55	1.5 – 6.0
			●	H	1	MC7125	HL	75 – 90	0.40 – 1.00	1.5 – 8.0
			●	H	2	MC7125	HM	75 – 90	0.50 – 1.10	2.0 – 10.0
			◐	L	1	MC7125	LM	95 – 120	0.10 – 0.35	0.3 – 2.0
			◐	L	2	MP7135	LM	70 – 95	0.10 – 0.35	0.3 – 2.0
			◐	L	3	MP7135	SH	70 – 95	0.10 – 0.40	0.3 – 2.0
			◐	M	1	MC7125	MM	90 – 110	0.15 – 0.45	0.7 – 5.0
			◐	M	2	MC7125	GM	90 – 110	0.16 – 0.50	0.5 – 4.0
			◐	M	3	MC7125	MA	90 – 110	0.10 – 0.30	0.5 – 3.0
			◐	M	4	MP7135	GM	65 – 90	0.16 – 0.50	0.5 – 4.0
			◐	M	5	MP7135	MM	65 – 90	0.15 – 0.45	0.7 – 5.0
			◐	M	6	MP7135	MA	65 – 90	0.10 – 0.30	0.5 – 3.0
			◐	R	1	MC7125	RM	85 – 100	0.25 – 0.55	1.5 – 6.0
			◐	R	2	MP7135	RM	60 – 85	0.25 – 0.55	1.5 – 6.0
			◐	R	3	MP7135	GH	60 – 85	0.25 – 0.60	1.5 – 6.0
			◐	H	1	MC7125	HL	75 – 90	0.40 – 1.00	1.5 – 8.0
			◐	H	2	MC7125	HM	75 – 90	0.50 – 1.00	2.0 – 10.0
			✣	L	1	MP7135	LM	70 – 95	0.10 – 0.35	0.3 – 2.0
			✣	L	2	MP7135	SH	70 – 95	0.10 – 0.40	0.3 – 2.0
			✣	M	1	MP7135	MM	65 – 90	0.15 – 0.45	0.7 – 5.0
			✣	R	1	MP7135	RM	60 – 85	0.25 – 0.55	1.5 – 6.0
			✣	R	2	MP7135	GH	60 – 85	0.25 – 0.60	1.5 – 6.0
			✣	H	1	MC7125	HL	75 – 90	0.40 – 1.00	1.5 – 8.0
			✣	H	2	MC7125	HM	75 – 90	0.50 – 1.10	2.0 – 10.0

1. Recommended cutting conditions for 5° / 7° / 11° positive inserts are provided as a guideline only.
   Verify the recommended conditions for each boring bar as cutting conditions for internal machining will vary depending on the length of overhang.

Cutting Conditions : ● : Stable cutting ◐ : General cutting ✣ : Unstable cutting

MC / MP7100 SERIES – 7° POSITIVE INSERTS (FOR EXTERNAL TURNING)

	Material	Hardness	Cutting mode	F L M R H	Priority	Grade		Vc	f	ap
M	Austenitic stainless steel	<200 HB	●	F	1	MC7115	FM	160 – 255	0.04 – 0.20	0.2 – 0.9
			●	F	2	MC7125	FM	150 – 210	0.04 – 0.20	0.2 – 0.9
			●	L	1	MC7125	LM	150 – 210	0.06 – 0.25	0.2 – 1.0
			●	L	2	MC7115	LM	160 – 255	0.06 – 0.25	0.2 – 1.0
			●	M	1	MC7125	MM	125 – 175	0.08 – 0.30	0.3 – 2.0
			●	M	2	MC7125	MV	125 – 175	0.08 – 0.30	0.3 – 2.0
			●	M	3	MC7115	MM	135 – 215	0.08 – 0.30	0.3 – 2.0
			◐	F	1	MC7125	FM	150 – 210	0.04 – 0.20	0.2 – 0.9
			◐	L	1	MC7125	LM	150 – 210	0.06 – 0.25	0.2 – 1.0
			◐	L	2	MP7135	LM	115 – 145	0.06 – 0.25	0.2 – 1.0
			◐	M	1	MC7125	MM	125 – 175	0.08 – 0.30	0.3 – 2.0
			◐	M	2	MC7125	MV	125 – 175	0.08 – 0.30	0.3 – 2.0
			✣	F	1	MP7135	FM	115 – 145	0.04 – 0.20	0.2 – 0.9
			✣	L	1	MP7135	LM	115 – 145	0.06 – 0.25	0.2 – 1.0
			✣	M	1	MP7135	MM	95 – 120	0.08 – 0.30	0.3 – 2.0
			✣	M	2	MP7135	MV	95 – 120	0.08 – 0.30	0.3 – 2.0
		200 HB	●	F	1	MC7115	FM	135 – 215	0.04 – 0.20	0.2 – 0.9
			●	F	2	MC7125	FM	125 – 175	0.04 – 0.20	0.2 – 0.9
			●	L	1	MC7125	LM	125 – 175	0.06 – 0.25	0.2 – 1.0
			●	L	2	MC7115	LM	135 – 215	0.06 – 0.25	0.2 – 1.0
			●	M	1	MC7125	MM	105 – 145	0.08 – 0.30	0.3 – 2.0
			●	M	2	MC7125	MV	105 – 145	0.08 – 0.30	0.3 – 2.0
			●	M	3	MC7115	MM	110 – 180	0.08 – 0.30	0.3 – 2.0
			◐	F	1	MC7125	FM	125 – 175	0.04 – 0.20	0.2 – 0.9
			◐	L	1	MC7125	LM	125 – 175	0.06 – 0.25	0.2 – 1.0
			◐	L	2	MP7135	LM	95 – 120	0.06 – 0.25	0.2 – 1.0
			◐	M	1	MC7125	MM	105 – 145	0.08 – 0.30	0.3 – 2.0
			◐	M	2	MC7125	MV	105 – 145	0.08 – 0.30	0.3 – 2.0
			✣	F	1	MP7135	FM	95 – 120	0.04 – 0.20	0.2 – 0.9
			✣	L	1	MP7135	LM	95 – 120	0.06 – 0.25	0.2 – 1.0
			✣	M	1	MP7135	MM	80 – 100	0.08 – 0.30	0.3 – 2.0
			✣	M	2	MP7135	MV	80 – 100	0.08 – 0.30	0.3 – 2.0
	Ferritic and martensitic stainless steel	<200 HB	●	F	1	MC7125	FM	150 – 210	0.04 – 0.20	0.2 – 0.9
			●	L	1	MC7125	LM	150 – 210	0.06 – 0.25	0.2 – 1.0
			●	L	2	MC7115	LM	160 – 255	0.06 – 0.25	0.2 – 1.0
			●	M	1	MC7125	MM	125 – 175	0.08 – 0.30	0.3 – 2.0
			●	M	2	MC7125	MV	125 – 175	0.08 – 0.30	0.3 – 2.0
			●	M	3	MC7115	MM	135 – 215	0.08 – 0.30	0.3 – 2.0
			◐	F	1	MC7125	FM	150 – 210	0.04 – 0.20	0.2 – 0.9
			◐	L	1	MC7125	LM	150 – 210	0.06 – 0.25	0.2 – 1.0
			◐	L	2	MP7135	LM	115 – 145	0.06 – 0.25	0.2 – 1.0
			◐	M	1	MC7125	MM	125 – 175	0.08 – 0.30	0.3 – 2.0
			◐	M	2	MC7125	MV	125 – 175	0.08 – 0.30	0.3 – 2.0
			✣	F	1	MP7135	FM	115 – 145	0.04 – 0.20	0.2 – 0.9
			✣	L	1	MP7135	LM	115 – 145	0.06 – 0.25	0.2 – 1.0
			✣	M	1	MP7135	MM	95 – 120	0.08 – 0.30	0.3 – 2.0
			✣	M	2	MP7135	MV	95 – 120	0.08 – 0.30	0.3 – 2.0

1. Recommended cutting conditions for 5° / 7° / 11° positive inserts are provided as a guideline only.
   Verify the recommended conditions for each boring bar as cutting conditions for internal machining will vary depending on the length of overhang.

Cutting Conditions : ● : Stable cutting ◐ : General cutting ✣ : Unstable cutting

MC/MP7100 SERIES – 7° POSITIVE INSERTS (FOR EXTERNAL TURNING)

	Material	Hardness	Cutting mode	F L M R H	Priority	Grade		Vc	f	ap
M	Ferritic and martensitic stainless steel	>200 HB	●	F	1	MC7125	FM	125 – 175	0.04 – 0.20	0.2 – 0.9
			●	F	2	MC7115	FM	135 – 215	0.04 – 0.20	0.2 – 0.9
			●	L	1	MC7125	LM	125 – 175	0.06 – 0.25	0.2 – 1.0
			●	L	2	MC7115	LM	135 – 215	0.06 – 0.25	0.2 – 1.0
			●	M	1	MC7125	MM	105 – 145	0.08 – 0.30	0.3 – 2.0
			●	M	2	MC7125	MV	105 – 145	0.08 – 0.30	0.3 – 2.0
			●	M	3	MC7115	MM	110 – 180	0.08 – 0.30	0.3 – 2.0
			◐	F	1	MC7125	FM	125 – 175	0.04 – 0.20	0.2 – 0.9
			◐	L	1	MC7125	LM	125 – 175	0.06 – 0.25	0.2 – 1.0
			◐	L	2	MP7135	LM	95 – 120	0.06 – 0.25	0.2 – 1.0
			◐	M	1	MC7125	MM	105 – 145	0.08 – 0.30	0.3 – 2.0
			◐	M	2	MC7125	MV	105 – 145	0.08 – 0.30	0.3 – 2.0
			✣	F	1	MP7135	FM	95 – 120	0.04 – 0.20	0.2 – 0.9
			✣	L	1	MP7135	LM	95 – 120	0.06 – 0.25	0.2 – 1.0
			✣	M	1	MP7135	MM	80 – 100	0.08 – 0.30	0.3 – 2.0
			✣	M	2	MP7135	MV	80 – 100	0.08 – 0.30	0.3 – 2.0
	Two-phase stainless steel	<280 HB	●	F	1	MP7135	FM	75 – 100	0.04 – 0.20	0.2 – 0.9
			●	L	1	MP7135	LM	75 – 100	0.06 – 0.25	0.2 – 1.0
			●	L	2	MC7125	LM	100 – 140	0.06 – 0.25	0.2 – 1.0
			●	L	3	MC7115	LM	110 – 175	0.06 – 0.25	0.2 – 1.0
			●	M	1	MP7135	MM	65 – 80	0.08 – 0.30	0.3 – 2.0
			●	M	2	MC7125	MM	85 – 115	0.08 – 0.30	0.3 – 2.0
			●	M	3	MC7125	MV	85 – 115	0.08 – 0.30	0.3 – 2.0
			●	M	4	MC7115	MM	90 – 145	0.08 – 0.30	0.3 – 2.0
			◐	F	1	MC7125	FM	100 – 140	0.04 – 0.20	0.2 – 0.9
			◐	L	1	MC7125	LM	100 – 140	0.06 – 0.25	0.2 – 1.0
			◐	M	1	MC7125	MM	85 – 115	0.08 – 0.30	0.3 – 2.0
			◐	M	2	MC7125	MV	85 – 115	0.08 – 0.30	0.3 – 2.0
			✣	F	1	MP7135	FM	75 – 100	0.04 – 0.20	0.2 – 0.9
			✣	L	1	MP7135	LM	75 – 100	0.06 – 0.25	0.2 – 1.0
			✣	M	1	MP7135	MM	65 – 80	0.08 – 0.30	0.3 – 2.0
			✣	M	2	MP7135	MV	65 – 80	0.08 – 0.30	0.3 – 2.0
	Precipitation-hardening stainless steel	450 HB	●	F	1	MC7115	FM	95 – 140	0.04 – 0.20	0.2 – 0.9
			●	L	1	MC7115	LM	95 – 140	0.06 – 0.20	0.2 – 1.0
			●	L	2	MC7125	LM	85 – 105	0.06 – 0.20	0.2 – 1.0
			●	M	1	MC7115	MM	80 – 120	0.08 – 0.25	0.3 – 2.0
			●	M	2	MC7125	MM	70 – 85	0.08 – 0.25	0.3 – 2.0
			◐	F	1	MC7125	FM	85 – 105	0.04 – 0.20	0.2 – 0.9
			◐	F	2	MP7135	FM	60 – 85	0.04 – 0.20	0.2 – 0.9
			◐	L	1	MC7125	LM	85 – 105	0.06 – 0.20	0.2 – 1.0
			◐	L	2	MP7135	LM	60 – 85	0.06 – 0.20	0.2 – 1.0
			◐	M	1	MC7125	MM	70 – 85	0.08 – 0.25	0.3 – 2.0
			◐	M	2	MC7125	MV	70 – 85	0.08 – 0.30	0.3 – 2.0
			◐	M	3	MP7135	MM	50 – 70	0.08 – 0.25	0.3 – 2.0
			✣	F	1	MP7135	FM	60 – 85	0.04 – 0.20	0.2 – 0.9
			✣	L	1	MP7135	LM	60 – 85	0.06 – 0.20	0.2 – 1.0
			✣	M	1	MP7135	MM	50 – 70	0.08 – 0.25	0.3 – 2.0
			✣	M	2	MP7135	MV	50 – 70	0.08 – 0.30	0.3 – 2.0

1. Recommended cutting conditions for 5° / 7° / 11° positive inserts are provided as a guideline only.
   Verify the recommended conditions for each boring bar as cutting conditions for internal machining will vary depending on the length of overhang.

Cutting Conditions : ● : Stable cutting ◐ : General cutting ✣ : Unstable cutting

MC/MP7100 SERIES – 11° POSITIVE INSERTS (FOR EXTERNAL TURNING)

Material	Hardness	Cutting mode	F L M R H	Priority	Grade		Vc	f	ap
M	Austenitic stainless steel	<200 HB	●	L	1	MC7125	LM	150 – 210	0.06 – 0.25	0.2 – 1.0
			●	L	2	MC7115	LM	160 – 255	0.06 – 0.25	0.2 – 1.0
			●	M	1	MC7125	MM	125 – 175	0.08 – 0.30	0.3 – 2.0
			●	M	2	MC7115	MM	135 – 215	0.08 – 0.30	0.3 – 2.0
			◐	L	1	MC7125	LM	150 – 210	0.06 – 0.25	0.2 – 1.0
			◐	M	1	MC7125	MM	125 – 175	0.08 – 0.30	0.3 – 2.0
			◐	M	2	MC7125	MV	125 – 175	0.08 – 0.30	0.3 – 2.0
			✣	L	1	MP7135	LM	115 – 145	0.06 – 0.25	0.2 – 1.0
			✣	M	1	MP7135	MM	95 – 120	0.08 – 0.30	0.3 – 2.0
			✣	M	2	MP7135	MV	95 – 120	0.08 – 0.30	0.3 – 2.0
		200 HB	●	L	1	MC7125	LM	125 – 175	0.06 – 0.25	0.2 – 1.0
			●	L	2	MC7115	LM	135 – 215	0.06 – 0.25	0.2 – 1.0
			●	M	1	MC7125	MM	105 – 145	0.08 – 0.30	0.3 – 2.0
			●	M	2	MC7125	MV	105 – 145	0.08 – 0.30	0.3 – 2.0
			●	M	3	MC7115	MM	110 – 180	0.08 – 0.30	0.3 – 2.0
			◐	L	1	MC7125	LM	125 – 175	0.06 – 0.25	0.2 – 1.0
			◐	M	1	MC7125	MM	105 – 145	0.08 – 0.30	0.3 – 2.0
			◐	M	2	MC7125	MV	105 – 145	0.08 – 0.30	0.3 – 2.0
			✣	L	1	MP7135	LM	95 – 120	0.06 – 0.25	0.2 – 1.0
			✣	M	1	MP7135	MM	80 – 100	0.08 – 0.30	0.3 – 2.0
			✣	M	2	MP7135	MV	80 – 100	0.08 – 0.30	0.3 – 2.0
	Ferritic and martensitic stainless steel	<200 HB	●	L	1	MC7125	LM	150 – 210	0.06 – 0.25	0.2 – 1.0
			●	L	2	MC7115	LM	160 – 255	0.06 – 0.25	0.2 – 1.0
			●	M	1	MC7125	MM	125 – 175	0.08 – 0.30	0.3 – 2.0
			●	M	2	MC7125	MV	125 – 175	0.08 – 0.30	0.3 – 2.0
			●	M	3	MC7115	MM	135 – 215	0.08 – 0.30	0.3 – 2.0
			◐	L	1	MC7125	LM	150 – 210	0.06 – 0.25	0.2 – 1.0
			◐	M	1	MC7125	MM	125 – 175	0.08 – 0.30	0.3 – 2.0
			◐	M	2	MC7125	MV	125 – 175	0.08 – 0.30	0.3 – 2.0
			✣	L	1	MP7135	LM	115 – 145	0.06 – 0.25	0.2 – 1.0
			✣	M	1	MP7135	MM	95 – 120	0.08 – 0.30	0.3 – 2.0
			✣	M	2	MP7135	MV	95 – 120	0.08 – 0.30	0.3 – 2.0
		>200 HB	●	L	1	MC7125	LM	125 – 175	0.06 – 0.25	0.2 – 1.0
			●	L	2	MC7115	LM	135 – 215	0.06 – 0.25	0.2 – 1.0
			●	M	1	MC7125	MM	105 – 145	0.08 – 0.30	0.3 – 2.0
			●	M	2	MC7125	MV	105 – 145	0.08 – 0.30	0.3 – 2.0
			●	M	3	MC7115	MM	110 – 180	0.08 – 0.30	0.3 – 2.0
			◐	L	1	MC7125	LM	125 – 175	0.06 – 0.25	0.2 – 1.0
			◐	M	1	MC7125	MM	105 – 145	0.08 – 0.30	0.3 – 2.0
			✣	L	1	MP7135	LM	95 – 120	0.06 – 0.25	0.2 – 1.0
			✣	M	1	MP7135	MM	80 – 100	0.08 – 0.30	0.3 – 2.0
			✣	M	2	MP7135	MV	80 – 100	0.08 – 0.30	0.3 – 2.0

1. Recommended cutting conditions for 5° / 7° / 11° positive inserts are provided as a guideline only.
   Verify the recommended conditions for each boring bar as cutting conditions for internal machining will vary depending on the length of overhang.

Cutting Conditions : ● : Stable cutting ◐ : General cutting ✣ : Unstable cutting

MC/MP7100 SERIES – 11° POSITIVE INSERTS (FOR EXTERNAL TURNING)

	Material	Hardness	Cutting mode	F L M R H	Priority	Grade		Vc	f	ap
M	Two-phase stainless steel	<280 HB	●	L	1	MC7125	LM	100 – 140	0.06 – 0.25	0.2 – 1.0
			●	L	2	MC7115	LM	110 – 175	0.06 – 0.25	0.2 – 1.0
			●	M	1	MC7125	MM	85 – 115	0.08 – 0.30	0.3 – 2.0
			●	M	2	MC7125	MV	85 – 115	0.08 – 0.30	0.3 – 2.0
			●	M	3	MC7115	MM	90 – 145	0.08 – 0.30	0.3 – 2.0
			◐	L	1	MP7135	LM	75 – 100	0.06 – 0.25	0.2 – 1.0
			◐	L	2	MC7125	LM	100 – 140	0.06 – 0.25	0.2 – 1.0
			◐	M	1	MC7125	MM	85 – 115	0.08 – 0.30	0.3 – 2.0
			◐	M	2	MC7125	MV	85 – 115	0.08 – 0.30	0.3 – 2.0
			✣	L	1	MP7135	LM	75 – 100	0.06 – 0.25	0.2 – 1.0
			✣	M	1	MP7135	MM	65 – 80	0.08 – 0.30	0.3 – 2.0
			✣	M	2	MP7135	MV	65 – 80	0.08 – 0.30	0.3 – 2.0
	Precipitation-hardening stainless steel	450 HB	●	L	1	MC7125	LM	85 – 105	0.06 – 0.20	0.2 – 1.0
			●	L	2	MC7115	LM	95 – 140	0.06 – 0.20	0.2 – 1.0
			●	M	1	MC7125	MM	70 – 85	0.08 – 0.25	0.3 – 2.0
			●	M	2	MC7125	MV	70 – 85	0.08 – 0.30	0.3 – 2.0
			◐	L	1	MC7125	LM	85 – 105	0.06 – 0.20	0.2 – 1.0
			◐	M	1	MC7125	MM	70 – 85	0.08 – 0.25	0.3 – 2.0
			◐	M	2	MC7125	MV	70 – 85	0.08 – 0.30	0.3 – 2.0
			✣	L	1	MP7135	LM	60 – 85	0.06 – 0.20	0.2 – 1.0
			✣	M	1	MC7125	MM	70 – 85	0.08 – 0.25	0.3 – 2.0
			✣	M	2	MC7125	MV	70 – 85	0.08 – 0.30	0.3 – 2.0

8/8

1. Recommended cutting conditions for 5° / 7° / 11° positive inserts are provided as a guideline only.
   Verify the recommended conditions for each boring bar as cutting conditions for internal machining will vary depending on the length of overhang.

Cutting Conditions : ● : Stable cutting ◐ : General cutting ✣ : Unstable cutting